Appl. No. 10/516,550 Amendment/Response Reply to Final Office action of 26 February 2007

Listing of Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

- 1. (previously presented) An electric lamp comprising:
- a glass lamp vessel which is closed in a gastight manner by means of a seal and which contains an electric element,

current conductors made at least partly from molybdenum, and connected to said electric element, which conductors are partly embedded in the seal and at least those portions which are in contact with the atmosphere outside the lamp are provided with means for protection against oxidation, characterized in that the means for protection against oxidation are chosen from the group of materials formed by chromium-manganese, chromium-cobalt, chromium-iron, and chromium-boron alloys.

- 2. (original) An electric lamp as claimed in claim 1, characterized in that the alloy contains 80 to 99 atom percents of chromium.
- 3. (original) An electric lamp as claimed in claim 1, characterized in that the alloy contains 94 to 96 atom percents of chromium.
- 4. (previously presented) An electric lamp as claimed in claim 1, characterized in that the alloy comprises chromium-manganese.
- 5. (previously presented) An electric lamp as claimed in claim
- 6, characterized in that the coating has a layer thickness of c:\PROFESSIONAL\PhilipsamDS2007\PHNL020466 116.doc

- at least 1µm and at most 6µm.
- 6. (previously presented) An electric lamp as claimed in claim 1, characterized in that means for protection against oxidation is a coating.
- 7. (previously presented) An electric lamp comprising:

a glass lamp vessel which is closed in a gastight manner by means of a seal and which contains an electric element,

current conductors made at least partly from molybdenum, and connected to said electric element, which conductors are partly embedded in the seal and are partly provided with means for protection against oxidation, the means for protection against oxidation being chosen from the group of materials formed by chromium-manganese, chromium-cobalt, chromium-iron, and chromium-boron alloys, characterized in that the alloy contains 80 to 99 atom percents of chromium.

8. (previously presented) An electric lamp as claimed in claim 7, characterized in that the alloy contains 94 to 96 atom percents of chromium.